

Chesapeake Minerals High-Purity Silica Sands are produced from high-purity raw quartz gravel with an extremely low iron content and few trace elements.

PW 200™ is crushed, milled and screened to maintain a size range between 140 and 400 Mesh. Liberated magnetic and paramagnetic minerals are removed with rare-earth roll magnets to maintain a consistent iron content below 80 ppm. The precise control of particle size distribution and chemistry improves production processes, allowing better control of production costs and compliance with customers' chemistry demands.

Because of its reliable chemical composition and consistent gradation quality, **PW 200™** is an excellent choice for a variety of applications requiring high-purity silica.

TYPICAL PARTICLE SIZE ANALYSIS (ASTM Sieve)	
140	2.7
200	10.3
230	15.0
270	19.0
325	18.2
400	20.7
PAN	11.4

PHYSICAL PROPERTIES	
Tapped Bulk Density (lb/ft ³)	89.5
Loose Bulk Density (lb/ft ³)	77.6
LOI %	0.054
% Moisture	<0.24
Specific Gravity (OD)	1.6
Water Absorption (%)	23.6
Magnetic Properties	Negative

TYPICAL COLOR PROPERTIES	
CIE Analysis- L	>88
a	0.5
b	0.8
Brightness	78.4
Whiteness Index	74.9
Yellowness Index	1.4

CHEMICAL ANALYSIS (Typical Median Reported as % by Weight)	
SiO ₂ (Silicon Dioxide)	>99.95%
Fe ₂ O ₃ (Ferric Oxide)	0.006
Al ₂ O ₃ (Aluminum Oxide)	0.035
TiO ₂ (Titanium Dioxide)	<0.0010 LLD
CaO (Calcium Oxide, Total)	<0.007
Cr ₂ O ₃ (Chromium Oxide)	<0.0005 LLD
K ₂ O (Potassium Oxide)	<0.0015 LLD
MgO (Magnesium Oxide)	<0.0025 LLD
Na ₂ O (Sodium Oxide)	<0.0050 LLD

TRACE CHEMISTRY (Typical - Reported as PPM)	
Pb (Lead)	<1.0
As (Arsenic)	<1.0
Ni (Nickel)	<1.0
Cr (Chromium)	<1.0
Cd (Cadmium)	<1.0
Hg (Mercury)	<1.0

CUSTOMER SERVICE:

P: 443.318.2872
E: info@chesapeakeminerals.com

SHIPPING:

- I-95: Halfway between Baltimore & Philadelphia
- CSX Rail System

DISTRIBUTION:

- Bulk shipment by Truck and Rail